



# MUDGE FASTENERS, INC.

## ASTM A449



### Scope

ASTM A449 covers headed bolts, rods, and anchor bolts in diameters ranging from 1/4" through 3" inclusive. It is a medium strength bolt manufactured from a medium carbon or alloy steel that develops its mechanical values through a heat treating process. It is intended for general engineering applications. ASTM A449 is virtually identical in chemistry and strength to ASTM A325 and SAE J429 grade 5. However, A449 is more flexible in the sense that it covers a larger diameter range and is not restricted by a specific configuration.

### Types

<b>TYPE 1</b>	Plain carbon steel, carbon boron steel, alloy steel, or alloy boron steel.
<b>TYPE 2</b>	Withdrawn 2003
<b>TYPE 3</b>	Weathering steel.

### Mechanical Properties

Size	Tensile, ksi	Yield, ksi	Elong. %, min	RA %, min
1/4-1	120 min	92 min	14	35
1-1/8 - 1-1/2	105 min	81 min	14	35
1-5/8 - 3	90 min	58 min	14	35

### Chemical Properties

Type 1 Bolts				
Element	Carbon Steel	Carbon Boron Steel	Alloy Steel	Alloy Boron Steel
Carbon	0.30 - 0.52%	0.30 - 0.52%	0.30 - 0.52%	0.30 - 0.52%
Manganese, min	0.60%	0.60%	0.60%	0.60%
Phosphorus, max	0.04%	0.04%	0.04%	0.04%
Sulfur, max	0.05%	0.05%	0.04%	0.04%
Silicon	0.15-0.30%	0.10 - 0.30%	0.15 - 0.35%	0.15 - 0.35%
Boron		0.0005 - 0.003%		0.0005 - 0.003%
Alloying Elements			*	*

\* Steel, as defined by the American Iron and Steel Institute, shall be considered to be alloy when the maximum range given for the content of alloying elements exceeds one of more of the following limits: Manganese, 1.65%, silicon, 0.60%, copper, 0.60%, or in which a definite range or a minimum quantity of any of the following elements is specified or required within the limits of the recognized field of constructional alloy steels: aluminum, chromium up to 3.99%, cobalt, columbium, molybdenum, nickel, titanium, tungsten, vanadium, zirconium or any other alloying elements added to obtain a desired alloying effect.

Type 3 Bolts, Class *						
Element	A	B	C	D	E	F
Carbon	0.33 - 0.40%	0.38 - 0.48%	0.15 - 0.25%	0.15 - 0.25%	0.20 - 0.25%	0.20 - 0.25%
Manganese	0.90 - 1.20%	0.70 - 0.90%	0.80 - 1.35%	0.40 - 1.20%	0.60 - 1.00%	0.90 - 1.20%
Phosphorus	0.035% max	0.06 - 0.12%	0.035% max	0.035% max	0.04%	0.04%
Sulfur, max	0.04%	0.04%	0.04%	0.04%	0.04%	0.04%
Silicon	0.15 - 0.35%	0.30 - 0.50%	0.15 - 0.35%	0.25 - 0.50%	0.15 - 0.35%	0.15 - 0.35%
Copper	0.25 - 0.45%	0.20 - 0.40%	0.20 - 0.50%	0.30 - 0.50%	0.30 - 0.60%	0.20 - 0.40%
Nickel	0.25 - 0.45%	0.50 - 0.80%	0.25 - 0.50%	0.50 - 0.80%	0.30 - 0.60%	0.20 - 0.40%
Chromium	0.45 - 0.65%	0.50 - 0.75%	0.30 - 0.50%	0.50 - 1.00%	0.60 - 0.90%	0.45 - 0.65%
Vanadium			0.020% min			
Molybdenum		0.06% max		0.10% max		
Titanium				0.05% max		

\* Selection of a class shall be at the option of the manufacturer

### Recommended Nuts and Washers

Nuts				Washers
Plain		Galvanized		
1/4 - 1-1/2	1-5/8 - 3	1/4/2003		F436
A563B Hex	A563A Heavy Hex	A563DH Heavy Hex		

Note: Nuts of other grades having proof load stresses greater than the specified grade are suitable. The ASTM A563 Nut Compatibility

# WE GET IT RIGHT... RIGHT ON TIME